

**IMK****UNIVERSITY OF BELGRADE
FACULTY OF CIVIL ENGINEERING****INSTITUTE FOR MATERIALS AND STRUCTURES
Laboratory for Structures**Bulevar kralja Aleksandra 73, 11000 BELGRADE, Republic of Serbia
Phone: (+381-11) 33-70-152 Fax: (+381-11) 33-70-253 e-mail: office@imk.grf.bg.ac.rs**PRILOG uz I Z V O D iz Izveštaja / APENDIX of EXTRACT of the Report
Br./No .008/2012-131073/3 - 12**Tablica nosivosti limova TR 35/200 Lemind komerc d.o.o. Leskovac prema efektivnim karakteristikama preseka za
ugib $\leq L/200$ i napon $\sigma_{max} \leq 14 \text{ kN/cm}^2$ *Table of load carrying capacity of corrugated steel sheets TR 35/200 Lemind komerc ltd. Leskovac
based on cross section effective properties for deflection $\leq L/200$ and stress $\sigma_{max} \leq 14 \text{ kN/cm}^2$*

d	J_{eff}	W_{eff}	p	JEDAN RASPON /	DVA RASPONA /	TRI I VIŠE RASPONA /
				ONE SPAN	TWO SPANS	THREE AND MORE SPANS
mm	cm^4/m	cm^3/m	kN/m^2	L_{max}	L_{max}	L_{max}
				m	m	m
0.50	5.91	3.04	1.00	1.68	1.85	1.68
0.50	5.91	3.04	1.25	1.56	1.65	1.56
0.50	5.91	3.04	1.50	1.47	1.51	1.47
0.50	5.91	3.04	1.75	1.39	1.39	1.39
0.50	5.91	3.04	2.00	1.30	1.30	1.30
0.55	6.65	3.42	1.00	1.75	1.96	1.75
0.55	6.65	3.42	1.25	1.62	1.75	1.62
0.55	6.65	3.42	1.50	1.53	1.60	1.53
0.55	6.65	3.42	1.75	1.45	1.48	1.45
0.55	6.65	3.42	2.00	1.38	1.38	1.38
0.60	7.78	4.15	1.00	1.84	2.16	1.84
0.60	7.78	4.15	1.25	1.71	1.93	1.71
0.60	7.78	4.15	1.50	1.61	1.76	1.61
0.60	7.78	4.15	1.75	1.53	1.63	1.53
0.60	7.78	4.15	2.00	1.46	1.52	1.46
0.70	9.50	5.25	1.00	1.97	2.42	1.97
0.70	9.50	5.25	1.25	1.83	2.17	1.83
0.70	9.50	5.25	1.50	1.72	1.98	1.72
0.70	9.50	5.25	1.75	1.64	1.83	1.64
0.70	9.50	5.25	2.00	1.56	1.71	1.56
0.80	11.28	6.33	1.00	2.09	2.66	2.09
0.80	11.28	6.33	1.25	1.94	2.38	1.94
0.80	11.28	6.33	1.50	1.82	2.17	1.82
0.80	11.28	6.33	1.75	1.73	2.01	1.73
0.80	11.28	6.33	2.00	1.66	1.88	1.66
1.00	14.82	8.33	1.00	2.29	3.05	2.29
1.00	14.82	8.33	1.25	2.12	2.73	2.12
1.00	14.82	8.33	1.50	2.00	2.49	2.00
1.00	14.82	8.33	1.75	1.90	2.31	1.90
1.00	14.82	8.33	2.00	1.81	2.16	1.81